



ALOY FCL

Specifications June 13, 2025

COUNTRY OF ORIGIN	China		
PERFORMANCE FINISH	YES		
FIBER CONTENT	OVERALL	100%POLYE	
	FACE	N/A	
	BACK	N/A	
CONSTRUCTION	18 Ends Per Inch	16 Picks Per Inch	
WIDTH	54"		
WEIGHT	Approx. 1.373 lbs. per linear yard		
RAILROADED	Y		
PATTERN REPEAT	WARP N/A"	FILL N/A"	

Performance Standards

SEAM BREAKING STRENGTH	WARP/FILL	79/83 lbs	ASTM D-4034 MIN. 50 LBS
TEAR STRENGTH	WARP/FILL	24/19 lbs	ASTM D-2261-13 MIN. 6 LBS
SEAM SLIPPAGE	WARP/FILL	52/40 lbs	ASTM D-4034 MIN. 25 LBS
TENSILE STRENGTH	WARP/FILL	104/95 lbs	ASTM D-5034 MIN. 50 LBS
ABRASION	Heavy Duty – 50,000 Cycles (Wyzenbeck - Wire Screen Abradant)		ASTM D-4157 MIN. 9000 CYCLES
PILLING	Class 4		ASTM D-3511 MIN. CLASS 3
UFAC	Class I		
CALIFORNIA TECHNICAL BULLETIN 117-2013	Pass		PASS or FAIL
COLORFASTNESS TO LIGHT	40 Hours – Class 4		AATCC-16A CLASS 3 or ABOVE
COLORFASTNESS TO CROCKING	DRY – Class 4.0 WET – Class 4.5		AATCC-8 MIN. CLASS 4.0 (DRY), CLASS 3.0 (WET)
DYNAMIC SEAM FATIGUE	Pass 5,000 Cycles		ASTM D-4033

*Culp pattern test results are compliant to listed Fabric Standards and referenced testing methods.

Cleaning Code **W** - Spot clean only with water based shampoo or foam upholstery cleaner. Pretest a small, inconspicuous area before proceeding. Do not overwet. Do not use solvents to spot clean. Pile fabrics may require brushing with a non-metallic, stiff bristle brush to restore appearance. Hot water extraction or steam cleaning is not a recommended cleaning method. Cushion covers should not be removed and laundered. To prevent overall soiling, frequent vacuuming or light brushing with a non metallic, stiff bristle brush to remove dust and grime is recommended. When cleaning a spill, blot immediately to remove spilled material. Clean spots or stains from the outside to the middle of the affected area to prevent circling. Use a professional furniture cleaning service when an overall soiled condition has been reached.