



CULP

TEST DATE: JANUARY 14, 2024

PATTERN: SHARELLE PL

FIBER CONTENT:	(Face) 100%POLYE (Overall) 100%POLYE (Back) 100%POLYE	
COUNTRY OF ORIGIN:	China	
CONSTRUCTION:	28 Picks Per Inch 40 Ends Per Inch	<u>Standards</u>
WIDTH:	54"	MIN. 54 INCHES
WEIGHT:	Approx. 1.405 lbs. per linear yard	
*CLEANING CODE:	"W"	
SEAM BREAKING STRENGTH: (ASTM D-4034)	Warp/Filling 95/95	MIN. 50 LBS
TEAR STRENGTH: (ASTM D-2261-13)	Warp/Filling 51/30	MIN. 6 LBS
SEAM SLIPPAGE: (ASTM D-4034)	Warp/Filling 69/34	MIN. 25 LBS
TENSILE STRENGTH: (ASTM D-5034)	Warp/Filling 234/134	MIN. 50 LBS
ABRASION: (ASTM D-4157)	Heavy Duty - 30,000 Cycles (Wyzenbeck - Wire Screen Abradant)	MIN. 9000 CYCLES
PILLING: (ASTM D-3511)	Class 4	MIN. CLASS 3
UFAC:	Class I	
CALIFORNIA TECHNICAL BULLETIN 117-2013	Pass	PASS or FAIL
COLORFASTNESS TO LIGHT: (ASTM D-3597, AATCC-16A)	40 Hours - Class 3	CLASS 3 OR ABOVE
COLORFASTNESS TO CROCKING: (ASTM D-3597, AATCC-8)	Dry - Class 4.5 Wet - Class 4.5	MIN CLASS 4 MIN CLASS 3
DYNAMIC SEAM FATIGUE: (ASTM D-4033)	Pass 5,000 Cycles	MIN 5000 CYCLES
FABRIC GRADE:	A	
RAILROADED:	Y	
THEORETICAL PATTERN REPEAT:	WARP N/A" FILL N/A"	AGREED UPON AT PURCHASE

- Culp pattern test results are compliant to listed Fabric Standards and referenced testing methods.



"Spot clean only with water based shampoo or foam upholstery cleaner. Pretest a small, inconspicuous area before proceeding. Do not overwet. Do not use solvents to spot clean. Pile fabrics may require brushing with a non-metallic, stiff bristle brush to restore appearance. Hot water extraction or steam cleaning is not a recommended cleaning method. Cushion covers should not be removed and laundered. To prevent overall soiling, frequent vacuuming or light brushing with a non metallic, stiff bristle brush to remove dust and grime is recommended. When cleaning a spill, blot immediately to remove spilled material. Clean spots or stains from the outside to the middle of the affected area to prevent circling. Use a professional furniture cleaning service when an overall soiled condition has been reached."