

DECEMBER 12, 2014

PATTERN: SUNSET VALLEY

| | | |
|-------------------------------------------|------------------------------------------------------------------|--------------------|
| FIBER CONTENT: | (Face) | 85%POLYE15%RYN |
| | (Backing) | 100% ACRYLIC BLEND |
| CONSTRUCTION: | 82 | Picks Per Inch |
| | 160 | Ends Per Inch |
| WIDTH: | 54.0" | |
| WEIGHT: | Approx. 1.462 lbs. per linear yard | |
| *COLORFASTNESS CODE: | "W" | |
| SEAM BREAKING STRENGTH: (ASTM D-4034) | Warp/Filling | 105/77 |
| TEAR STRENGTH: (ASTM D-2262) | Warp/Filling | 19/39 |
| SEAM SLIPPAGE: (ASTM D-4034) | Warp/Filling | 58/52 |
| TENSILE STRENGTH: (ASTM D-5034) | Warp/Filling | 141/304 |
| ABRASION: (ASTM D-4157) | Medium Duty - 9,000 Cycles (Wyzenbeck - Wire Screen Abradant) | |
| PILLING: (ASTM D-3511) | Class 3 | |
| UFAC: | Class I | |
| CALIFORNIA TECHNICAL BULLETIN 117-2013 | Pass | |

COLORFASTNESS TO LIGHT: 40 Hours - Class 4
(ASTM D-3597, AATCC-16A)

COLORFASTNESS TO CROCKING: Dry - Class 4
(ASTM D-3597, AATCC-8) Wet - Class 3

Page 2

PATTERN: SUNSET VALLEY

Date: DECEMBER 12, 2014

Grade: B

Theoretical Repeat:

Warp: 28.5"

Fill: 18.7"

DYNAMIC SEAM FATIGUE: Pass 5,000 Cycles
(ASTM D-4033)

- * "Spot clean only with water based shampoo or foam upholstery cleaner. Pretest a small, inconspicuous area before proceeding. Do not overwet. Do not use solvents to spot clean. Pile fabrics may require brushing with a non-metallic, stiff bristle brush to restore appearance. Hot water extraction or steam cleaning is not a recommended cleaning method. Cushion covers should not be removed and laundered. To prevent overall soiling, frequent vacuuming or light brushing with a non metallic, stiff bristle brush to remove dust and grime is recommended. When cleaning a spill, blot immediately to remove spilled material. Clean spots or stains from the outside to the middle of the affected area to prevent circling. Use a professional furniture cleaning service when an overall soiled condition has been reached."